

Ink for Untreated Soft Aluminum Foil/ Cap Seal MH Ink

MH Ink, OP varnish ink, is used for untreated soft aluminum. It excels in various physical properties such as water resistance, heat resistance, etc. , and is primarily used for cap seals.

Main Resin	Cellulose Resin
Diluent	Toluene/Isopropyl alcohol/ Ethyl acetate=35/25/40 (MH No.2 Solvent) Toluene/Isopropyl alcohol/ Ethyl acetate/ Propylene glycol monomethyl ether=35/25/20/20 (MH No.4 Solvent)
OP Varnish	MH No.17 OP Varnish
	MH No.5 OP Varnish

■ Application

Untreated soft aluminum foil

■ Handling Instructions

Adjust the drying property by mixing it with MH No.2 and MH No.4 when blurring occurs due to high humidity in rainy season or when brushing occurs due to high temperature in summer.



- ▶ The data contained herein are based on the results of the tests conducted in accordance with the in-house test methods, and are not standard values. Always conduct pre-use tests to ascertain the suitability of the product to your requirements. Nothing contained herein is to be construed as a recommendation for use in violation of any patents, applicable laws or regulations. It is the responsibility of the user to comply in all respects with applicable laws and regulations.
- ▶ Owing to product improvement the information contained herein may be modified without any prior notice.
- ▶ Make sure to read MSDS thoroughly before using the product.